

LithoPore® LPAC Roof Insulation



www.blauer-engel.de/uz132

- low emissions
- low pollutant content
- no adverse impact on health in the living environment

Contact

LithoPore Europe GmbH
Goerzallee 309
14167 Berlin
Germany

Email: info@lithopore.com

Product description

LithoPore® - LPAC Roof Insulation is an aerated insulation materials for flat roofs or roofs with slight slope. It can be easily applied with mobile equipment. LithoPore® - LPAC Roof Insulation has to be applied in combination with a water-proofing layer also in case of humid regions. On the surface normally tiles or other ceramic products can be placed.

Highlights

- Fireproofed (totally inorganic)
- Fully recyclable (ordinary construction waste)
- Quick application



Specification

Metric	LithoPore400-600		
	Standard	entity	value
dry bulk density $\rho_{105\text{ }^{\circ}\text{C}}$	DIN EN 1602 [2]	[kg/m ³]	400-600
thermal conductivity $\lambda_{10, \text{tr}}$	DIN EN 12667 [13]	[W/mK]	0,10 - 0,17
compressive strength $\sigma_{10\%}$	DIN EN 826 [4]	[MPa]	1.0-3.0

Imperial	LithoPore400-600		
	standard	entity	value
dry bulk density $\rho_{105\text{ }^{\circ}\text{C}}$	ASTM C 1693	[pcf]	25-37.5
thermal conductivity $\lambda_{10, \text{tr}}$	ASTM C 177 ASTM C 518	[R-value per in]	0.9-1.5
compressive strength $\sigma_{10\%}$	ASTM C 1693	[PSI]	147-441



The information contained in this product specification is based on our current state of knowledge and experience. It does not free the user from making his own tests and trial applications. A legally binding assurance of certain properties cannot be inferred from this information. Any existing patent rights as well as any pertinent legal regulations must be observed by the recipient of our products under his own responsibility.